



INTELLATHANE

PRO

Protective Coating System

DESCRIPTION

Intellathane Pro is an all-purpose, 100% solids, spray applied elastomeric protective coating. Intellathane Pro offers a cost-effective balance of physical and mechanical properties as well as sprayability. Intellathane Pro is a pure urethane system that contains zero VOCs and exhibits excellent adhesion to wood, metal, and concrete substrates.

TYPICAL PHYSICAL PROPERTIES

Property	ISO Component	Poly Component
Brookfield Visc. @78° F, 20 RPM	800 CPS	800 CPS
Weight/Gallon	9.54 LBS	8.50 LBS
Color	Yellow	Multiple
Processing Data		
Mix Ratio (Parts by Vol.)	1	
String-Gel Time	5 Seconds	
Dry-To-Touch Time	8 Seconds	
Cured Property	Test Method	Result
Color		Multiple
Durometer	ASTM D2240	55 Shore D
Tensile Strength	ASTM D412	2,000 psi
Elongation	ASTM D5034	200%
Die-C Tear Strength	ASTM D624	300 pli
Dolly Adhesion	ASTM D4541	1,600 psi
Abrasion Resistance	ASTM D4060	-0.30% @ 1,000 cycles
Moisture Vapor Transmission, Perms	ASTM E96 (Procedure B)	1.67 @ 50 MILS

CHEMICAL RESISTANCE, 7-DAY SPOT TESTING

	Durometer Change	Appearance Change	Adhesion Change
Gasoline	A	A	B
Diesel Fuel #2	A	B	A
Motor Oil, Regular	A	A	A
Motor Oil, Full Synthetic	B	C	B
Motor Oil, Heavy/'Diesel'	A	A	A
Antifreeze 50:50, Water	A	B	A
Lacquer Thinner	B	B	B

CHEMICAL RESISTANCE RATING

A	B	C	D
No Loss	Minimal Loss	Slight Loss	Severe Loss

APPLICATION REQUIREMENTS

Spray Equipment: Spray equipment must be designed to produce a minimum of 2,500-psi with an output of 1.5 gallons per minute. The heating component of the equipment must be able to maintain a temperature at the gun of 150°F. The hose on the equipment must be heated and be rated a minimum of 3,000-psi burst pressure. The spray gun must also be rated at the pressures and throughputs required.

Substrate Parameters: The substrate must be dry! Proper substrate prep is critical to application success! A minimum ambient temperature of 5°F above the dew point is mandatory. The ambient relative humidity should not be above 85%. Product working temperature range is -40°F - 280°F. Pin-holing may occur if the above parameters are not strictly followed; it is up to the applicator to check initial climatic conditions. It is recommended that a small area be sprayed and checked for proper application.

Coverage: The material theoretically will cover 1,604 square feet at 100 mil dry film thickness. Coverage of the substrate should include a waste factor based on conditions at the site and type of substrate to which the material is being applied.

Storage: Liquid materials should be stored at temperatures between 55°F and 95°F in sealed containers. The A-side component should always be blanketed with nitrogen gas. Zero VOC's as packaged for A-side and B-side components. Material shelf-life is 6 to 12 months. Consult product SDS for proper safety and handling procedures of components.

DISCLAIMER: THE DATA PRESENTED HEREIN IS NOT INTENDED FOR USE BY NONPROFESSIONAL APPLICATORS, OR THOSE PERSONS WHO DO NOT PURCHASE OR UTILIZE THIS PRODUCT IN THE NORMAL COURSE OF THEIR BUSINESS. THE POTENTIAL USER MUST PERFORM ANY PERTINENT TEST IN ORDER TO DETERMINE THE PRODUCT'S PERFORMANCE AND SUITABILITY IN THE INTENDED APPLICATION, SINCE FINAL DETERMINATION OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR USE IS THE RESPONSIBILITY OF THE BUYER.

CALL CARLISLE POLYURETHANE SYSTEMS FOR TECHNICAL QUESTIONS. (888) 899-9665.

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. CARLISLE POLYURETHANE SYSTEMS WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES. CARLISLE POLYURETHANE SYSTEMS EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE CARLISLE POLYURETHANE SYSTEMS OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.

