

TRU-MOTION H3313

TDI/MDI TRACK BINDER

Tru-Motion H3313 is a 100% solids, TDI/MDI combination, moisture cure polyurethane binder for use in the construction of bonded rubber granule running tracks and similar athletic surfaces. Tru-Motion H3313 is carefully controlled for TDI content during manufacturing to minimize regulatory and construction site safety hazards associated with the use of TDI containing systems. It is designed to have optimized handling characteristics for track installation combined with high physical properties.

TYPICAL PROPERTIES AND CHARACTERISTICS

H3313

PHYSICAL CHARACTERISTICS

Appearance	Water clear viscous fluid
Density	8.8 – 9.0 lbs./Gal.
Viscosity	1,700 – 3,000 cps
% Free NCO	8.97 – 9.97 %
% Solids by Wt.	>99%

PHYSICAL PROPERTIES OF CURED FILMS

Tensile Strength (ASTM D412)	3,500+/-350 psi
Elongation (ASTM D412)	700+/-50%
Die C Tear (ASTM D624)	334+/-30 pli

PROCESSING

Tru-Motion H3313 TDI/MDI track binder is designed for application using conventional track installation equipment. Tru-Motion H3313 TDI/MDI track binder cures by reaction with atmospheric moisture. Cure rate is accelerated by high humidity and temperatures and retarded by low humidity and temperatures. Under extreme conditions of low humidity and temperature, water misting or catalyst addition may be required. Contact us for specific recommendations.

SAFETY AND HANDLING

Consult SDS before handling and observe all recommended safety, handling and disposal recommendations.

THIS PRODUCT CONTAINS TDI AND IS FOR INDUSTRIAL OR COMMERCIAL USE ONLY. NOT FOR USE BY CONSUMERS OR SALE OR RESALE TO CONSUMERS.

PACKAGING

Tru-Motion H3313 is available in 5-gallon pails, 55-gallon drums and 250-gallon totes.

STORAGE

Protect from moisture. Avoid prolonged storage at temperatures over 90° F or below 50° F. Under conditions of proper storage, the storage life of factory sealed containers is 12 months.

DISCLAIMER: THE DATA PRESENTED HEREIN IS NOT INTENDED FOR USE BY NON-PROFESSIONAL APPLICATORS, OR THOSE PERSONS WHO DO NOT PURCHASE OR UTILIZE THIS PRODUCT IN THE NORMAL COURSE OF THEIR BUSINESS. THE POTENTIAL USER MUST PERFORM ANY PERTINENT TEST IN ORDER TO DETERMINE THE PRODUCT'S PERFORMANCE AND SUITABILITY IN THE INTENDED APPLICATION: FINAL DETERMINATION OF QUALIFICATION FOR SAID PRODUCT IN ANY PARTICULAR APPLICATION IS THE RESPONSIBILITY OF THE BUYER/USER.

CALL CARLISLE POLYURETHANE SYSTEMS FOR TECHNICAL QUESTIONS.
(888) 899-9665.

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. CARLISLE POLYURETHANE SYSTEMS WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES. CARLISLE POLYURETHANE SYSTEMS EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE CARLISLE POLYURETHANE SYSTEMS OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.