



## TRU-MOTION H3617

### ALIPHATIC MOISTURE CURE BINDER

Tru-Motion H3617 is the fastest reacting aliphatic binder in the Tru-Motion aliphatic series. It is designed for installation at low temperature and low humidity. Tru-Motion H3617 is not appropriate for use at high temperatures. Also, it should not be stored and shipped at elevated temperatures or stored for more than three months.

Tru-Motion H3617 is a 100% solids, aliphatic isocyanate based, moisture cure binder for use in construction of bonded rubber granule type running tracks, athletic and safety surfaces.

Tru-Motion H3617 exhibits excellent color fastness and exterior durability allowing the use of light-colored EPDM granules without the objectionable yellowing encountered when using MDI and TDI binders. In addition, Tru-Motion H3617 exhibits improved resistance to deterioration by water and pool chemicals, making it the surfacing material of choice in areas subject to water and chemical immersion.

Tru-Motion H3617 is a primary skin irritant and can cause sensitization dermatitis. Avoid skin contact and wear proper protective equipment at all times when handling Tru-Motion H3617. Consult SDS before use and observe all recommended safety and handling practices.

#### TYPICAL PROPERTIES AND CHARACTERISTICS

##### Tru-Motion H3617

#### PHYSICAL CHARACTERISTICS

Appearance	Light yellow viscous fluid
Density (lbs./gal)	8.6-8.9
Viscosity	3,000-5,000 cps
% Free NCO	7.0-8.2%
Tensile Strength (ASTM D 412)	3,000 +/- 300 psi
Elongation (ASTM D 412)	500 +/- 50%
Die C Tear (ASTM D 624)	260 +/- 26 pli
Split Tear	55 +/- 5 pli

#### PROCESSING:

Under normal conditions of installation, Tru-Motion H3617 binder for granular rubber athletic surface products provides excellent work life while achieving sufficient cure for secondary processing within normal construction cycles.

Tru-Motion H3617 binder for granular rubber athletic surface products is designed to cure by reaction with atmospheric moisture. Cure rate is accelerated by high humidity and temperatures and retarded by low humidity and temperatures.

Under conditions of high temperature and low humidity, water misting of the applied surfaces immediately after installation will prevent the Tru-Motion H3617 from draining off the granular rubber components.

Tru-Motion H3617 as supplied has a work life suitable for use in safety surfaces under conditions of low temperature and low humidity.

**CAUTION:** Any colored EPDM granule mixture used with Tru-Motion H3617 should be evaluated for color change and reactivity rate before installation. Bromine will discolor all installed PIP surfacing.

#### SAFETY AND HANDLING:

- Wear proper protective equipment at all times.
- Tru-Motion H3617 is a primary skin irritant and can cause sensitization dermatitis. Avoid contact with skin and eyes. Wear proper protective equipment at all times when handling Tru-Motion H3617.
- In the event of eye contact, flush eyes thoroughly with water and seek medical attention.
- Consult SDS before handling and observe all recommended safety and handling procedures.
- Pressure can build up in new and previously opened containers, open all containers carefully.
- Protect open containers from moisture.
- Dispose of contaminated materials and empty containers in accordance with Federal, State and Local regulations



## TECHNICAL DATA

### PACKAGING:

Tru-Motion H3617 is available in 55-gallon closed head drums with a net weight of 450 lbs. and 5-gallon pails with a net weight of 43 lbs. Returnable and one-way 250-gallon mini-bulk containers are available on a special order basis.

### STORAGE:

Tru-Motion H3617 should be stored in cool, dry surroundings. Avoid prolonged storage temperatures over 90° F or below 40° F. Under conditions of proper storage, storage life of the product in original, factory sealed containers is 3 months.

DISCLAIMER: THE DATA PRESENTED HEREIN IS NOT INTENDED FOR USE BY NON-PROFESSIONAL APPLICATORS, OR THOSE PERSONS WHO DO NOT PURCHASE OR UTILIZE THIS PRODUCT IN THE NORMAL COURSE OF THEIR BUSINESS. THE POTENTIAL USER MUST PERFORM ANY PERTINENT TEST IN ORDER TO DETERMINE THE PRODUCT'S PERFORMANCE AND SUITABILITY IN THE INTENDED APPLICATION: FINAL DETERMINATION OF QUALIFICATION FOR SAID PRODUCT IN ANY PARTICULAR APPLICATION IS THE RESPONSIBILITY OF THE BUYER/USER.

CALL CARLISLE POLYURETHANE SYSTEMS FOR TECHNICAL QUESTIONS.  
(888) 899-9665.

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. CARLISLE POLYURETHANE SYSTEMS WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES. CARLISLE POLYURETHANE SYSTEMS EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE CARLISLE POLYURETHANE SYSTEMS OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.

### CARLISLE POLYURETHANE SYSTEMS

2500 Adie Road  
Maryland Heights, MO 63043  
314.872.8700 | 888.899.9665

